



NORDFEED

## Magnesium Oxide ( Caustic Calcined Magnesite ) - MgO

Magnesium Oxide (MgO)	min.83,5 %
Magnesium (Mg) *	min.51.0 %
Silicon Dioxide (SiO <sub>2</sub> )	max.8.0 %
Calcium Oxide (CaO)	max.4.0 %
Iron (III) Oxide (Fe <sub>2</sub> O <sub>3</sub> )	max.1,5 %
Aluminium (III) Oxide (Al <sub>2</sub> O <sub>3</sub> )	max.0,5%
Loss on ignition	max.4%
Grain Size	0 – 1 mm

Arsenic (As)	max.20 mg/kg
Cadmium (Cd)	max.2.0 mg/kg
Fluorine (F)	max.600 mg/kg
Lead (Pb)	max.10 mg/kg
Mercury (Hg)	max.0,1 mg/kg
Nitrites (as Sodium nitrite)	max.15 mg/kg

Dioxins (ng WHO-PCCD/F-TEQ/kg)	max.0,75 ng/kg
Dioxins+PCBs (ng WHO-PCDD/F-PCB-TEQ/kg)	max.1.0 ng/kg
Non-Dioxin like PCBs	max.10µg/kg

(\*) calculated from MgO

REACH Registered

The given information is based on our most recent knowledge. These are typical property values and are intended as guides only, not as specification limits. Users are advised to conduct their own test and evaluation to determine the safety and suitability for their own purposes. This document does not constitute a warranty or guarantee

### CONTACT

e-mail : [info@nordfeed.com](mailto:info@nordfeed.com)

web : [www.nordfeed.com](http://www.nordfeed.com)

phone : +90 532 5407833



NORDFEED

CONTACT

e-mail : [info@nordfeed.com](mailto:info@nordfeed.com)

web : [www.nordfeed.com](http://www.nordfeed.com)

phone :+90 532 5407833